

## Vialit Test Report

**Laboratory Reference:** DUD11B-0191-2

**Client:** Otech

**Adhesion Agent:** Aggbind

**Adhesion Agent Source:** Otech

**Aggregate Source:** Winton

**Binder Used:** 180/200

**Tested By:** Tony Horsfall

**Test Method Used:** WCSL B301-89T (DRAFT) Vialit Test (Not Accredited)


**Specification:** TNZ M13 Specification for Adhesion Agent 1989

### Results

AA Dosage pph by volume	Adhesion Agent Type	Result	T Value
1.3	Aggbind 60	88	0.4
1.3	Aggbind 75	94	0.3
Specification		$\geq 80$	$\leq 2$

Washed Grade 3 chip used, passing 13.2mm retained 9.5mm

Issued By:



Date:

9 JUNE 2011