

Otech Adhesion Agents Summary of Work to date

Aggregate	Adhesion Agent	Dosage pph	Result
Logan Point	Aggbind Exp 60	1.0	94
Oamaru Shingle	Aggbind Exp 60	1.0	97
Parkburn	Aggbind Exp 60	1.0	100
Balclutha	Aggbind 75	1.0	82
BHQ Blackhead	Aggbind 75	1.0	65

The above testwork was carried out at the Fulton Hogan Dunedin Laboratory, under the instructions of Tony Horsfall